

ViterBond ST200 Epoxy ST Primer

Product Description	A two pack epoxy, high solids, surface tolerant aluminium primer.				
Features & Use	<ul style="list-style-type: none"> • Use as a rust inhibiting primer on hand prepared steel, or as a high build patch repair primer under most generic coating types • Approved to UK Network Rail specification as the primer of a 3 coat system applied to manually prepared steelwork • Excellent anticorrosive protection • Excellent 'wetting' properties for application to a manually prepared steel surface • Good chemical and solvent resistance • Use to upgrade a conventional system to high performance epoxy/polyurethane system • Use as a single coat system under insulation (see Product Notes) 				
Approvals/ Certification	UK Network Rail M24 (Item 7.1.5)				
Finish	Sheen				
Volume Solids	80 ± 2%				
VOC Content	182 ± 20 g/litre				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Minimum	125 µm	157 µm	6.4 m ² /litre	
	Maximum	200 µm	250 µm	4.0 m ² /litre	
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated					
Drying Times	Applied to 125 microns DFT	+10°C	+23°C	+35°C	
	Dust Free	10 hr	4 hr	2 hr	
	Hard Dry	24 hr	16 hr	8 hr	
	Overcoating*	Minimum	See Product Notes		
		Maximum	Indefinite if clean and sound, with itself or ViterBond WG500		
* See Product Notes Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation					
Colours	Dark Aluminium				
Mix Ratio/ Product Code	Base	3332 001	1 part by volume		
	Hardener	4056 006	1 part by volume		
Pot Life	2 hours at 23°C				
SG	1.28 – 1.32 kg/lit mixed				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	23-60°C				

ViterBond ST200 Epoxy ST Primer

<p>Surface Preparation</p>	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Blast clean to Sa2½ (ISO 8501-1:2007), surface profile 50-75 microns Where blast cleaning is impractical the surface should be prepared to St2 (ISO 8501-1:2007) taking care to avoid 'polishing' the surface Can be used as a brush or spray applied primer when water abrasive blast cleaning. Allow to dry and lightly wire brush if powdery deposits form 														
<p>Mixing</p>	<p>Mix only in the proportions stated, mixing each component individually then together using a mechanical agitator. Agitate periodically during use to ensure product remains homogeneous.</p>														
<p>Thinner</p>	<p>1031 Thinner</p>		<p>Equipment Cleaner 950 Thinner</p>												
<p>Application Conditions</p>	<p>Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Only apply this product when the above conditions can be maintained throughout the critical application and drying/curing process. Paint temperature should ideally be at a minimum of 15°C.</p>														
<p>Application Methods</p>	<table border="1" data-bbox="451 965 1489 1088"> <thead> <tr> <th data-bbox="451 965 692 1032">Method</th> <th data-bbox="692 965 938 1032">Airless Spray</th> <th data-bbox="938 965 1184 1032">Conventional Spray</th> <th data-bbox="1184 965 1337 1032">Brush</th> <th data-bbox="1337 965 1489 1032">Roller</th> </tr> </thead> <tbody> <tr> <td data-bbox="451 1032 692 1088"></td> <td data-bbox="692 1032 938 1088">Yes</td> <td data-bbox="938 1032 1184 1088">No</td> <td data-bbox="1184 1032 1337 1088">Yes</td> <td data-bbox="1337 1032 1489 1088">No</td> </tr> </tbody> </table> <ul style="list-style-type: none"> Airless Spray: Output fluid pressure at tip 2000-3000 psi, Tip Size: 19-27 thou (0.48-0.68mm). Apply by brush over manually prepared bare steel surfaces If applying by brush over blast cleaned steel, take care not to brush the coating off the peaks, or apply two brush coats for safety Refer to Axalta Coating Systems 'Epoxy Application and Curing Notes' 					Method	Airless Spray	Conventional Spray	Brush	Roller		Yes	No	Yes	No
Method	Airless Spray	Conventional Spray	Brush	Roller											
	Yes	No	Yes	No											
<p>Product Notes</p>	<ul style="list-style-type: none"> Overcoating with conventional, chlorinated rubber or vinyl: ideally overcoat between 24-48 hours at 23°C. Maximum is 7 days or abrading is required Overcoating with epoxy or two pack polyurethane: min 24 hours, max 3 months, at 23°C Overcoating with alkyds: starting with ViterLac AM112 MIO is recommended for good intercoat adhesion. Min 24 hours, max 7 days, or abrading will be required Overcoating with itself or ViterBond WG500: whilst this product will not fully effectively cure below 10°C, overcoating by spray, with itself or ViterBond WG500, after 16 hours at 5°C minimum is acceptable Extend min/max drying and overcoating times at lower temperatures and for dft's above 125 microns Under insulation the product is suitable for dry operating temperatures up to 150°C with occasional surges to 200°C Do not apply or cure below 5°C. See ViterBond WG200 for low temperature applications Colour changes can occur in exposed conditions and will occur at elevated temperatures Moisture in the can may cause pressure build up 														
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>														

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.